

Temperature		Annealed Copper Resistance Correction Factor
°C	°F	multiply by
15	59	1.0200
16	60.8	1.0161
17	62.6	1.0119
18	64.4	1.0079
19	66.2	1.0039
20	68	1.0000
20.5	68.9	0.9980
21	69.8	0.9961
21.5	70.7	0.9941
22	71.6	0.9922
22.5	72.5	0.9903
23	73.4	0.9883
23.5	74.3	0.9864
24	75.2	0.9845
24.5	76.1	0.9826
25	77	0.9807
25.5	77.9	0.9789
26	78.8	0.9769
26.5	79.7	0.9751
27	80.6	0.9732
27.5	81.5	0.9713
28	82.4	0.9696
28.5	83.3	0.9677
29	84.2	0.9658
29.5	85.1	0.9640
30	86	0.9622
30.5	86.9	0.9603
31	87.8	0.9585
32	89.6	0.9550
33	91.4	0.9514
34	93.2	0.9478
35	95	0.9443
36	96.8	0.9407
37	98.6	0.9374
38	100.4	0.9338
39	102.2	0.9305

40	104	0.9271
----	-----	--------